



TRIM, DOOR & CABINETY INTERIOR/EXTERIOR SEMI-GLOSS PAINT



PRODUCT INFORMATION

KILZ TRIBUTE® Trim, Door & Cabinetry Interior/Exterior Semi-Gloss Paint has excellent flow & leveling and dries to a hard, durable finish. It features a unique formula developed to offer the best characteristics of interior and exterior paint in one convenient product. With outstanding block resistance, it's ideal for cabinets, doors, trim, windows, shutters, and woodwork. This allows quicker return to service as the painted surfaces won't stick to each other after they dry. This paint can also be used on properly prepared and primed surfaces like drywall, masonry, and metal.

RECOMMENDED USES

Ideal for properly prepared and primed interior and exterior surfaces such as.

- Walls
- Ceilings
- Wood
- Engineered Wood
- Architectural Plastics
- Drywall/Gypsum Board
- Plaster
- Concrete
- Stucco
- Masonry
- Brick
- Concrete Masonry Units
- Steel
- Galvanized Steel
- Aluminum
- Other Metals

PRODUCT SPECIFICATIONS

T5951 White Base:

- 1 Gallon 124 fl oz / 6 fl oz
- 1 Quart 31 oz. / 1.5 oz.

T5953 Deep Base:

- 1 Gallon 116 fl oz / 10 fl oz
- 1 Quart 29 oz. / 2.5 oz.

Gloss: 40 – 50 @ 60°

Resin Type: Acrylic

Weight per Gallon: 10.9 lb

% Solids by Volume: 36% ± 2%

% Solids by Weight: 51% ± 2%

VOC: < 50 g/L

Flash Point: N/A

Viscosity: 85 – 95 KU

Recommended Film Thickness:

- 1st Coat Wet: 4.6 mils / Dry: 1.6 mils @ 350 sq ft/gal
- 2nd Coat Wet: 4.0 mils / Dry: 1.4 mils @ 400 sq ft/gal
- Two (2) coats are required for optimum protection.

Coverage: 350 – 400 sq ft/gal depending on application method and substrate porosity. Does not include the loss of material from spraying.

APPLICATION

Brush:

Nylon brush for best results

Roller:

1/4" nap roller cover

Airless Spray:

- Tip: .013" – .015"
- Filter: 60 mesh
- Fluid Pressure: 1,400 – 2,400 psi

Thinning: DO NOT THIN. Product is formulated for use at package consistency.

Dry Time: @ 77°F & 50% RH

To Touch: 1 hour

To Recoat: 2 hours

Full Cure: 7 days

Dry times are temperature, humidity, and film thickness dependent.

SURFACE PREPARATION

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust and all other foreign substances.

Wood:

WARNING! Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection. Remove mill glaze with sandpaper. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a wiping cloth. Fill all gaps with a paintable caulking and allow to completely dry prior to coating.

Drywall:

All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating.

Masonry:

All masonry surfaces must be cured at least 30 days before painting. The pH must be 10 or lower prior to coating. Remove bond breakers and all form release and curing agents. Smooth masonry may require an adequate profile for adhesion. For all other smooth trowel concrete, create an adequate profile for adhesion using a product such as muriatic acid etcher or with mechanical means.

COMPLIES WITH THE BELOW AS OF 10/1/2023			
SCAQMD	YES	AIM	YES
LADCO	YES	OTC Phase II	YES
CARB SCM 2007	YES	OTC	YES

Remove all loose aggregate and debris. If painting cannot wait 30 days or pH level is above 10, allow the surface to cure 7 days and prime the surface with an alkali-resistant primer.

New Plaster:

New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize. Prime the area with an alkali-resistant primer.

Previously Painted Plaster:

Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate spackling material and let dry completely and sand smooth. Remove all dust with a tack or wiping cloth. Fill all gaps with a paintable caulking, and allow to completely dry prior to coating.

Steel:

Minimum surface preparation is Hand Tool Cleaning in accordance with SSPC-SP2. Remove all oil and grease from the surface with a solvent in accordance with SSPC-SP1. For optimal performance, use Commercial Blast Cleaning in accordance with SSPC-SP6. Prime the area with a rust-inhibitive primer the same day as cleaned.

Galvanized Steel:

Solvent clean new galvanized metal in accordance with SSPC-SP1 to remove oil and grease from the surface. Pre-treat with a phosphoric acid solution or a commercially-available etching solution. Galvanized metal that has been passivated with chromates or silicates may require brush blasting in accordance with SSPC-SP16 to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning in accordance with SSPC-SP2. Prime the area the same day as cleaned.

Aluminum:

Remove all oil and grease from the surface with a solvent in accordance with SSPC-SP1. Prime the area the same day as cleaned.

\* Numbers given here are from Ultra Bright White/ Base 1. This information is provided "as is" and no representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information. For SDS or to consult with a technical service representative, call 1-866-275-5459 (1-866-ASK-KILZ) • kilz.com • ©2023 MasterChem Industries, LLC.

# KILZ TRIBUTE® TRIM, DOOR & CABINETS INTERIOR/EXTERIOR SEMI-GLOSS PAINT



## SURFACE PREPARATION *(CONTINUED)*

### Stain-Blocking:

For unpainted or heavily stained surfaces, prime using a product such as KILZ® PREMIUM Primer/sealer/stainblocker. After priming, test for stain bleed-through by applying the topcoat to a small section. If the stain bleeds through the topcoat, apply a second coat of primer and test again before top coating the entire area. If bleeding continues, a longer dry time of the primer may be needed before top-coating.

### Previously Painted Surfaces:

Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a tack or wiping cloth. Fill all gaps with a paintable caulking, and allow to completely dry prior to coating. Prime using a product such as KILZ® PREMIUM Primer/sealer/stainblocker.

### Glossy Surfaces:

For maximum adhesion, scuff and sand the surface thoroughly to provide a rough surface before coating.

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact Lead Information Center at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## CLEAN-UP/DISPOSAL

Clean all tools and equipment with warm, soapy water. Do not dispose of paint down a drain. For disposal of empty containers and unused product, contact your household refuse collection service.

## CAUTIONS/LIMITATIONS

- Protect from freezing.
- Do not use on floors.
- For best results, apply when air, material and surface temperatures are between 50°F and 90°F. Temperatures above 90°F can cause the paint to dry too fast, whereas temperatures below 50°F can inhibit proper film formation.
- Allow one week before washing or cleaning for full cure. The best approach to washing or cleaning the painted surface is to start with the least aggressive method, i.e., water on a soft cellulose sponge.
- Shelf life under normal conditions is two years unopened.
- Certain colors may require additional coats for complete hide.

## GENERAL INFORMATION:

**WARNING!** CAUSES EYE AND SKIN IRRITATION. MAY CAUSE RESPIRATORY TRACT IRRITATION. MAY CONTAIN: CRYSTALLINE SILICA AND TITANIUM DIOXIDE. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING VAPORS, SPRAY MIST AND SANDING DUST. Sanding, grinding or abrading may release sanding dust, which may be harmful if inhaled and has been shown to cause lung damage or cancer with long term exposure. Do not breathe dusts, vapor, or spray mist. To avoid breathing in dust, vapors, and spray mist, open windows and doors or use other means to ensure fresh air entry during application, drying, sanding, and/or abrading. If properly used, a respirator (NIOSH approved with particulate pre-filter) may offer additional protection and should be used if adequate ventilation cannot be provided; obtain professional advice before using. If you experience eye watering, headaches, or dizziness during application or drying, increase fresh air or leave the area. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use.

**FIRST AID:** If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 20 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

**KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.**

\* Numbers given here are from Ultra Bright White/ Base 1.

This information is provided "as is" and no representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information. For SDS or to consult with a technical service representative, call 1-866-275-5459 (1-866-ASK-KILZ) • [kilz.com](http://kilz.com) • ©2023 MasterChem Industries, LLC.